



GSE STANDARD PRODUCTS

Product Data Sheet

GSE UltraFlex

GSE UltraFlex is a high quality, linear low density polyethylene (LLDPE) geomembrane produced from specially formulated, virgin polyethylene with outstanding flexibility. This polyethylene resin is designed specifically for flexible geomembrane applications. Its high uniaxial and multiaxial elongation characteristics make it very suitable for applications where differential or localized subgrade settlements are expected such as leach pads, landfill closure caps, or any application where elongation or puncture resistance is critical. GSE UltraFlex contains approximately 97.5% polyethylene, 2.5% carbon black and trace amounts of antioxidants and heat stabilizers; no fillers or extenders are used. GSE UltraFlex is the only material of its type on the market with many years of proven performance in applications throughout the world. *These product specifications meet or exceed GRI GM17.*

Product Specifications

TESTED PROPERTY	TEST METHOD	FREQUENCY	MINIMUM VALUE			
Product Code			LLD 030A000	LLD 040A000	LLD 060A000	LLD 080A000
Thickness, (minimum average) mil (mm) Lowest individual reading (-10%)	ASTM D 5199	every roll	30 (0.75) 27 (0.69)	40 (1.00) 36 (0.91)	60 (1.50) 54 (1.40)	80 (2.00) 72 (1.80)
Density, g/cm ³	ASTM D 1505	200,000 lb	0.92	0.92	0.92	0.92
Tensile Properties (each direction) Strength at Break, lb/in-width (N/mm) Elongation at Break, %	ASTM D 6693, Type IV Dumbell, 2 ipm G.L. = 2.0 in (51 mm)	20,000 lb	114 (20) 800	152 (27) 800	228 (40) 800	304 (53) 800
Tear Resistance, lb (N)	ASTM D 1004	45,000 lb	16 (71)	22 (98)	33 (147)	44 (200)
Puncture Resistance, lb (N)	ASTM D 4833	45,000 lb	42 (190)	56 (250)	84 (370)	112 (500)
Carbon Black Content, %	ASTM D 1603	20,000 lb	2.0	2.0	2.0	2.0
Carbon Black Dispersion	ASTM D 5596	45,000 lb	+Note 1	+Note 1	+Note 1	+Note 1
REFERENCE PROPERTY	TEST METHOD	FREQUENCY	NOMINAL VALUE			
Oxidative Induction Time, min	ASTM D 3895, 200° C, 1 atm	200,000 lb	>100	>100	>100	>100
Roll Length (approximate), ft (m)			1,120 (341)	870 (265)	560 (171)	430 (131)
Roll Width ⁽¹⁾ , ft (m)			22.5 (6.9)	22.5 (6.9)	22.5 (6.9)	22.5 (6.9)
Roll Area ⁽¹⁾ , ft ² (m ²)			25,200 (2,341)	19,575 (1,819)	12,600 (1,171)	9,675 (899)

NOTES:

- +Note 1: Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- GSE UltraFlex is available in rolls weighing about 3,800 lb (1,724 kg) respectively.
- All GSE geomembranes have dimensional stability of ±2% when tested with ASTM D 1204 and ITB of <-77° C when tested with ASTM D 746.
- ⁽¹⁾Roll lengths and widths have a tolerance of ± 1%.

DS003 UltraFlex R03/07/06

This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures and specifications.

GSE and other trademarks in this document are registered trademarks of GSE Lining Technology, Inc. in the United States and certain foreign countries.

North America	GSE Lining Technology, Inc.	Houston, Texas	800 435 2008	281 443 8564	Fax: 281 230 8650
South America	GSE Lining Technology Chile S.A.	Santiago, Chile		56 2 595 4200	Fax: 56 2 595 4290
Asia Pacific	GSE Lining Technology Company Limited	Bangkok, Thailand		66 2 937 0091	Fax: 66 2 937 0097
Europe & Africa	GSE Lining Technology GmbH	Hamburg, Germany		49 40 767420	Fax: 49 40 7674234
Middle East	GSE Lining Technology-Egypt	The 6th of October City, Egypt		202 2 828 8888	Fax: 202 2 828 8889